




solid solutions to better hardscapes

PO Box 70 • 32020 126th St • Princeton, MN 55371 • Tel 800-752-9326 • Fax 763-389-2725

SRW NW4.5



Product Specification

SRW Products Manufactures/Supplies a 100% Polypropylene Non-Woven produced by needle punching staple fibers in a random network to form a high strength dimensionally stable fabric. The polypropylene material is specially formulated to resist ultraviolet light deterioration, and is inert to commonly encountered soil chemicals. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents.

SRW NW4.5 meets or exceeds the physical property values listed below.

Fabric Property	Test Method	Units	Minimum Average Roll Value
Weight (Typical)	ASTM D 5261	oz/yd ²	4.2
Grab Tensile	ASTM D 4632	lbs.	120
Grab Elongation	ASTM D 4632	lbs.	50
Trap-Tear Strength	ASTM D 4533	lbs.	50
Mullen Burst Strength	ASTM D 3786	psi	240
Puncture	ASTM D 4833	lbs.	70
Permittivity	ASTM D 4491	sec ⁻¹	1.8
Water Flow	ASTM D 4491	gpm/ft ²	120
UV Resistance	ASTM D 4355	%	70
AOS	ASTM D 4751	US Sieve	#70

To the best of our knowledge, the information contained herein is accurate. However, SRW Products cannot anticipate all conditions under which SRW product information and our products or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety or suitability of our products either alone or in combination with other products. Final determination of the suitability of any information or material for the used contemplated, or its manner of use, and whether the suggested use infringes any patents is the sole responsibility of the user.